

• 4119 White Bear Parkway, St. Paul, MN 55110 USA
• Phone (651) 429-1100, Fax (651) 429-1122
• Toll Free (800) 4-CORTEC, E-mail info@corotecvci.com
• Internet <http://www.corotecvci.com>

Comparing Corrosion Protection of VpCI-377 and Richclean 10-65A Used by Systrand Manufacturing

- Background:** Systrand Manufacturing specializes in a variety of metal manufacturing processes, including cast iron, steel forging, and die cast aluminum. Systrand currently uses Richclean 10-65A as a cleaner/rust preventative for their parts, and they have been having corrosion issues. The corrosion protection of the Richclean product will be compared to VpCI-377.
- Purpose:** Compare, in the humidity cabinet, the corrosion protection of VpCI-377 to Richclean 10-65A, which is currently used by Systrand Manufacturing.
- Method:** ASTM D-1748 humidity cabinet
- Materials:** Two differential cases, provided by Systrand Manufacturing
Richclean 10-65A (concentrate)
VpCI-377
VpCI-126 Blue film
- Procedure:** The following procedure was used:
- 1) The differential cases arrived and were visually inspected.
 - 2) One case was dipped in a 10% solution of Richclean 10-65A.
 - 3) The second case was dipped in a 5% solution of VpCI-377
 - 4) Both cases were allowed to dry overnight.
 - 5) The cases were then placed in VpCI-126 Blue film bags, which were then heat sealed.
 - 6) Both cases were then placed in ASTM D-1748 humidity cabinet.
 - 7) The cases were visually inspected periodically.
 - 8) After 336 hours, both cases were removed from ASTM D-1748 humidity cabinet.
 - 9) Both cases were removed from VpCI-126 bags, visually inspected, and photographed.
- Results:** The following results were found:
- 1) The case treated with Richclean 10-65A began to corrode after 72 hours. After 336 hours, corrosion was present on greater than 75% of the surface area.
 - 2) The case treated with VpCI-377 showed a small amount of corrosion after 336 hours. The corrosion present totaled less than 1% of the surface area of the piece, and was located on the underside of the part.
- Conclusion:** VpCI-377 provided superior corrosion protection on differential cases in humidity testing, when compared to Richclean 10-65A. Furthermore, VpCI-377 was used at half the concentration of the Richclean product.





Part dipped in 10% Richclean 10-65A, after 336 hours in ASTM D-1748 humidity cabinet.



Part dipped in 5% VpCI-377, after 336 hours in ASTM D-1748 humidity cabinet.